

## ULTRATEC LAMINATING RESINS

Product Code: C200003 – C200012



## PRODUCT DESCRIPTION

These resins are thixotropic, pre-promoted products available in unwaxed and LSE form which are specifically designed for high performance Marine and Transport applications using hand lay-up and spray application.

These resins have rapid glass fibre wetting properties, excellent sprayability and reduced tendency towards shrinkage problems such as pre-release while giving fast cure performance and maintaining a relatively wide green time, low exotherm and low colour in thick sections.

The LSE versions of these products contain a combination of additives which improve the working environment during and after application by substantially reducing styrene evaporation, while providing excellent interlaminar adhesion characteristics after delayed lay-up.

## VARIANTS

PRODUCT	DESCRIPTION
C200003	ULTRATEC LAMINATING RESIN 30'
C200004	ULTRATEC LSE LAMINATING RESIN 30'
C200005	ULTRATEC LAMINATING RESIN 45'
C200006	ULTRATEC LSE LAMINATING RESIN 45'
C200007	ULTRATEC LAMINATING RESIN 60'
C200008	ULTRATEC LSE LAMINATING RESIN 60'
C200009	ULTRATEC LAMINATING RESIN 75'
C200010	ULTRATEC LSE LAMINATING RESIN 75'
C200011	ULTRATEC LAMINATING RESIN 90'
C200012	ULTRATEC LSE LAMINATING RESIN 90'

## PROPERTIES

Contain ingredients which reduce styrene emission during application and give the cured laminate a tack-free surface. Low styrene emission resins alone will not enable the user to comply with the recommended atmospheric styrene levels, but with appropriate ventilation, these resins may assist in reducing the level of styrene in the workshop to which workers are exposed.

When a laminate is built up in stages with intermediate curing, each operation should be finished with a normal resin/glass fibre ratio. Excellent interlaminar adhesion properties have been demonstrated with **ULTRATEC**, following delays between lay-ups of up to 7 days. However, since conditions vary from workshop to workshop, the intervals between successive laminating operations should not exceed 48 hours unless the surface is abraded, (to ensure optimum secondary bonding). Any areas with an excess of resin should be abraded in any case if further laminates are to be applied.

## TYPICAL LIQUID RESIN PROPERTIES

PROPERTY	TYPICAL VALUE
Appearance	Opaque Blue, Clean
Brookfield LVT2/12 Viscosity @25°C	1600 - 2000cP
Cone and Plate viscosity @23°C	210 - 250cP
Density	1.10 g/m <sup>3</sup>
Flash Point (Setaflash)	31°C
Volatile Content, %	40-44
Styrene Emission, g/m <sup>2</sup> (LSE Versions only)	<20
Stability without initiator	6 months

## TYPICAL CAST UNFILLED RESIN PROPERTIES

Test	Result	Test Method
Barcol Hardness (GYZ 934-1)	40+	EN 59
Density	1.19 g/cm <sup>3</sup>	ISO R1183
Volume Shrinkage	7%	ISO 3521
Tensile strength, MPa	60	ISO R527
Flexural strength, MPa	100	ISO 178
Flexural modulus, GPa	4	ISO 178
Elongation at break %	2	ISO R527
Heat deflection temperature (1.8MPa), °C	65	ISO 75
Water absorption:		
One day, (mg)	15	ISO 62
Seven days, (mg)	22	ISO 180

\* Cast resin was prepared as laid down in BS 3532 using 1% MEKP. Cured at room temperature for sixteen hours then post cured for two hours at 80°C followed by two hours at 100°C.

## STORAGE AND HANDLING

To ensure maximum stability and maintain optimum resin handling properties, polyester resins should be stored in closed containers, away from heat sources and sunlight. The resin should be stored away from all sources of ignition. Stored resin quantities should be kept to a reasonable minimum and used on a first in/first out stock rotation basis. Prolonged storage, or unfavourable storing conditions, may cause separation, therefore agitation of the resin before use is recommended.

## STANDARD PACKAGING

Mild steel drums (225kg)

Always refer to the MSDS before use.

**DISCLAIMER:** This information appearing in this Document (**Details**) concerning the product which is the subject of the Document (**Product**) is either based on present technical knowledge and tests done by allnex or tests done by, and data supplied from third parties including you, the customer. Since the actual use by you and by others of the Product is beyond the control of allnex, no warranty or representation, express or implied is made by allnex regarding the suitability for such use, nor does allnex accept any liability arising out of the use by you of other products or materials, whether third party or not, that may be referred to in this Document. allnex recommends that you carry out your own tests as to the suitability of the Product for your purpose, regarding which you accept full responsibility. In addition, if any of the Details appearing in the Document are based upon tests done by, and/or data supplied by any third party, allnex provides no warranties or representations in connection with those Details and you, the customer waives any right you may have against allnex in connection with the accuracy, completeness or otherwise of the Details. The information in this Document is not to be construed as absolutely complete or accurate since additional information may be necessary or desirable when particular or exceptional conditions or circumstances exist or because of applicable laws or government regulations affecting use of the Product. allnex does not provide any warranty or representation to you that the Product does not infringe the intellectual property rights of any third party. All orders accepted shall be subject to the standard conditions of sale of allnex which are on the back of our invoice. In accepting the Product you, the customer acknowledge and agree: **a.)** The Product is or may be of a hazardous nature and that you, the customer, are responsible for the disposal of the container housing the Product in accordance with the requirements and regulations of the relevant supervising government. **b.)** The Product has a limited shelf life and must be stored strictly in accordance with the guidelines and specifications related to it. **c.)** Where the Details relate to Product tested by allnex, those Details are indicative only, regarding which there may be batch to batch variation. **d.)** allnex gives no warranty or representation as to the applicability for the particular use by you, the customer, of the Product and you the customer shall be responsible for ensuring that the Product is fit for your intended use. **e.)** allnex's liability for breach of any term, condition, guarantee or warranty (express or implied) concerning the information in this Document or the Product more generally including any liability for direct or indirect consequential loss (including indirect loss of profits), is limited to the maximum extent permitted by law and, at allnex's election, to either replacing or repairing the goods or paying the cost of replacing or repairing the goods, or in the case of services, supplying the services again.